

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase.
Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

SAFETY PRECAUTIONS

Read label before use. Keep out of reach of children. May cause damage to organs through prolonged or repeated exposure.

PRECAUTIONS

DO NOT BREATHE MISTS, VAPOURS OR SPRAYS. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions.

FIRST AID

IF SWALLOWED: Call a POISON CENTRE, doctor or first aider if you feel unwell.

IF ON SKIN (or hair): Wash with plenty of soap and water. If skin irritation occurs get medical advice.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue rinsing. If eye irritation persists get medical advice or attention.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing. If experiencing respiratory symptoms call a POISON CENTRE, doctor or first aider.

If exposed or concerned: Call a POISON CENTRE, doctor or first aider.

When seeking medical advice take this container with you. Further information can be obtained from

AUST: POISONS INFORMATION CENTRE 131 126
or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)
or call Resene 0800 737 363.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet D506.

SPILLS: Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible onto newspaper before washing brushes and rollers. Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.

WARNING

KEEP OUT OF REACH OF CHILDREN

Resene

Qristal ClearFloor 1K

waterborne flooring urethane interior



9 418022 034643

SATIN

Resene Qristal ClearFloor 1K is a waterborne urethane durable flooring finish designed to protect your wooden flooring and keep it looking its best for longer.

Preparation

- Ensure surfaces to be coated are in a sound condition, free from dirt, dust, loose material, oil, grease and floor polishes.

- Stop all nail holes and cracked timber with a suitable filler.
- Thoroughly sand surfaces prior to coating. Finish off with fine sandpaper, remembering to sand with the grain.

- For best results total removal of previously varnished surfaces is recommended to ensure a uniform appearance. Alternatively sand old sound varnish to remove all gloss and provide a key for good adhesion. Non uniform colour will be created when a new clear coating is applied to a floor that has areas of bare timber and old varnish.

- Thoroughly vacuum all surfaces to remove loose surface contaminants and sanding dusts. Pay special attention to sanding dusts and residual floor polish in the gaps between tongue and groove flooring.

- All sanding dusts may be harmful and appropriate protection must be worn. In particular sanding dusts from old lead or chromate based paints or old asbestos containing building materials may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.

- This product is designed for application to timber or timber composite flooring. If the surface you propose to coat is unsound or not referred to consult your nearest Resene ColorShop or reseller for your nearest Resene Technical Representative.

- Apply by synthetic brush or Resene Waterborne Clears roller sleeve.

- Apply at recommended spreading rate in an even manner to achieve a uniform wet film thickness and lay-off with at least a 50% overlap. To avoid increasing entrained air, do not overwork the wet film.

- Recoating can be undertaken when the applied coating is no longer milky in appearance and does not leave a fingerprint when pressed.

- Lightly sand with 240 grit sandpaper prior to application of the final coat of clear.

- Drying is dependent upon temperature and humidity, poor ventilation may inhibit curing and performance.

- Do not use gas or diesel burners to heat coated area as these produce water that will inhibit drying.

Be PaintWise
For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information.

Resene
the paint the professionals use

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 918, Ashmore City, QLD 4214
Ph 1800 738 383 Visit resene.com.au

In New Zealand: Resene Paints Limited
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045
Ph (04) 577 0500 Visit resene.co.nz

Made in manufacturing facilities which comply with ISO 9001 and ISO 14001. Printed on paper produced in manufacturing facilities which comply with environmental management systems EMAS and ISO 14001, using vegetable-based inks. Please recycle.

Apply at recommended spreading rate in an even manner to achieve a uniform wet film thickness and lay-off with at least a 50% overlap. To avoid increasing entrained air, do not overwork the wet film.

Recoating can be undertaken when the applied coating is no longer milky in appearance and does not leave a fingerprint when pressed.

Lightly sand with 240 grit sandpaper prior to application of the final coat of clear.

Drying is dependent upon temperature and humidity, poor ventilation may inhibit curing and performance.

Do not use gas or diesel burners to heat coated area as these produce water that will inhibit drying.

Be PaintWise
For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information.

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 918, Ashmore City, QLD 4214
Ph 1800 738 383 Visit resene.com.au

In New Zealand: Resene Paints Limited
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045
Ph (04) 577 0500 Visit resene.co.nz

Made in manufacturing facilities which comply with ISO 9001 and ISO 14001. Printed on paper produced in manufacturing facilities which comply with environmental management systems EMAS and ISO 14001, using vegetable-based inks. Please recycle.

Quick check

Use on: Timber or timber composite flooring.

Gloss level: Satin.

Coverage (average): 10 square metres per litre per coat at 30 microns. Spreading rates are given for bare timber – take care not to overspread on sealed timber.

Dry time (minimum): Tack free 1.5 hours at 18°C. Drying is affected by low temperatures and high humidity. Do not apply at temperatures below 10°C or when temperatures are liable to drop below this during the drying period. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 2 hours at 18°C.

Primer required: No.

Usual number of coats: Three for light traffic areas, four for heavy traffic areas.

Application method: Synthetic brush or roller (Resene Waterborne Clears sleeve). Not suitable for application to vertical surfaces.

Thinning: Do not thin, supplied at application viscosity.

Clean up: Warm water and detergent.

Colour range: Milky – dries clear.

Before use: Stir well before and regularly during use with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy. In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. Resene products are designed to be used as a system for optimal results. Substitution may cause substandard results or system failure. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.