


Always use correct Personal Protective Equipment


ENAMEL ADD

Description




Enamel Add is a clear colourless Aliphatic Isocyanate resin solution used as an additive for Spraying Enamel. The additive improves hardness chemical resistance, gloss, durability and dry times of conventional spraying enamels.

Products



Product Type:	Additive hardener for RALI Spraying Enamel
Colour:	Clear
Pot Life:	
Induction Time:	5 min when added to RALI Spraying Enamel, then re stir product
Density:	N/A
Recommended DFT:	N/A
Theoretical Coverage:	

Directions For Use



Add 500mls of Enamel Add to 4 litres of Spraying Enamel. Mix in well. Allow standing five minutes before use. Thin as normal manner with Spraying Thinner or Winter Thinners (refer Spraying Enamel data sheet)

PRECAUTIONS: When opened the contents of Enamel Add should be used as soon as possible. The life of the contents will be extended provided the screw cap is replaced firmly immediately after use. Excessive moisture contamination will cause the contents to foam and/or gel rendering Enamel Add unsuitable for use.


Health & Safety



For detailed information refer to Safety Data Sheet (SDS). Contains Isocyanates, avoid contact with skin and eyes.

Avoid breathing vapour. Use protective clothing and respiratory equipment. Product is flammable.

Transport & Storage



Sizes:	500 ml
Dangerous Goods:	6.1(a)
UN:	1263
Hazchem:	3W E
Packing Group:	II
Shipment name:	PAINT Related Material (Flammable)
Flash point:	Below 23°C

No warranty either expressed or implied is made by RALI in this document, which is a technical data information sheet. The description of the product and its properties is for the sole purpose of identifying the product and does not constitute a warranty that the product or its properties shall conform to that description, nor is the description of the product and its properties a warranty by RALI that the goods are suitable for a particular purpose. Do not apply paint if relative humidity is above 85% or temperature is within 3 deg C of Dew Point being the MPT or Minimum Paint Temperature.