

net contents 500ml

A-L1379850 6/13

KEEP OUT OF REACH OF CHILDREN

WARNING

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation.

PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods of cleaning equipment and disposing of unwanted paint. Do not contaminate any water supply.

FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE or doctor/physician if you feel unwell.

IF ON SKIN (or hair): Remove/take off all contaminated clothing and wash before re-use. Rinse skin with plenty of soap and water/shower. If skin irritation or rash occurs: Get medical advice/attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do so. Continue rinsing. If eye irritation persists: Get medical attention/advice.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing.

When seeking medical advice take this container with you.

Further information can be obtained from

AUST: POISONS INFORMATION CENTRE 131 126

or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)

or call Resene 0800 737 363.

For use as a decorative/protective coating.

SPILLS: Wear appropriate clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.

Resene blackboard paint

waterborne exterior/interior



Resene Blackboard Paint is a premium washable waterborne coating for interior and exterior smooth wallboards and panels where a hardwearing blackboard coating is required. Use only with high quality blackboard chalk using a blackboard duster or soft cloth to remove chalk. If you wish to use Liquid Chalk, use a Resene Write-On Wall Paint system instead of Resene Blackboard Paint.

Preparation

- Ensure surfaces to be painted are in sound condition, thoroughly sanded to a smooth finish, dry, free from dirt, dust and loose material.
- If mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80).
- **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old building materials containing asbestos may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**

• Plasterboard must be prepared to an appropriate level of finish. Either Resene Broadwall Surface Prep & Seal (see Data Sheet D807), Resene Broadwall 3 in 1 (see Data Sheet D810) or Resene Sureseal (see Data Sheet D42) followed by lining paper is recommended in critical lighting areas

• This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or Reseller for advice.

Priming

- Resene Quick Dry must be used as the first coat on fibre and particle boards.
- Plasterboard and stoppings should be primed (e.g. Resene Broadwall Waterborne Wallboard Sealer - see Data Sheet D403). Fibrous plaster should be sealed with Resene Sureseal.
- Hardboard must be sealed (e.g. Resene Sureseal) to promote flow of the topcoats. Use Resene Sureseal if the surface is water stained or if condensation is likely to form on the surface.
- Some 'soft' plasterboard preparatory products

and undercoated gypsum based stoppings may not be suitable basecoats for painting under stressed conditions. Reinforcement with a saturation coat of a fully penetrating primer (such as Resene Sureseal) may be required. Use Resene Sureseal or Resene StainLock (see Data Sheet D408) if the surface is water stained or has yellowed due to prolonged exposure to sunlight.

- All surfaces (except timber) which are in poor condition, affected by efflorescence, friable, powdery or chalky must be primed with Resene Sureseal.
- Sound fibre cement surfaces do not normally require a primer. Spot prime any nailheads with Resene Galvo-Prime (see Data Sheet D402).
- Repaints - spot prime all bare areas with the same primer shown for new work and proceed as for new work.

Application

- Prepare and prime the surface. Apply two topcoats of Resene Blackboard Paint by brush, roller or spray.
- Maintain good ventilation throughout the drying and post application curing period to ensure the paint is properly cured. This may require use of an extraction system when painting in marginal painting conditions. Do not use gas or diesel burners to heat coated area as these produce water that will inhibit drying and curing. Poor ventilation may affect appearance and performance..

Be PaintWise

For tips on minimising the impact of your decorating on the environment see the Resene website.



the paint the professionals use

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 924, Beenleigh, Qld 4207
Phone 1800 738 383 Fax 1800 064 960
Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Phone (04) 577 0500 Fax (04) 577 0600
Email advice@resene.co.nz or visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

Quick check

Use on: A premium washable waterborne coating for interior and exterior smooth wallboards and panels where a hardwearing blackboard coating is required.

Gloss level: Low sheen - fully washable. Not for use on opening sashes and doors.

Coverage: 12 square metres per litre per coat.

Dry time (minimum): 30 minutes. Do not apply at temperatures below 10°C or when temperatures are liable to drop below this during drying period. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 3 hours.

Primer required: Dependent on surface.

Usual number of coats: Two.

Application method: Brush, speed brush, roller or spray.

Thinning: In hot conditions may be thinned with up to 5% Resene Hot Weather Additive to slow drying.

Clean up: Water.

Colour range: Black, blue, green and pink. For other colour options, Resene SpaceCote Low Sheen can also be used as a blackboard finish.


Before use: Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.

Colour range:



Black



Green



Pink



Blue

Colours are as close as printing process allows. For other colour options, Resene SpaceCote Low Sheen can also be used as a blackboard finish.