

Resene Polythane

clear polyurethane

Resene Polythane is a single pack hardwearing moisture-cured polyurethane. Optimum clear gloss finish for floors and hardwearing surfaces because of its unique combination of flexibility and abrasion resistance. Exceptional flow properties.

interior

Typical uses

- Concrete formwork
- Cork and parquet flooring
- Corridors
- Fibre and particle board
- Gymnasiums
- Halls
- Indoor courts
- Timber
- Work floors

Vehicle type	Moisture-cured polyurethane
Pigmentation	None
Solvent	Aromatic
Pot life	See limitations
Finish	Gloss
Colour	Clear
Dry time (minimum)	3 hours
Recoat time (minimum)	3 hours, maximum of 24 hours; after the second coat film should be lightly sanded to ensure good intercoat adhesion
Sealer required	Yes, for fibre and particle board
Theoretical coverage	8-12 sq. metres per litre
Dry film thickness	43 microns at 8 sq. metres per litre 28 microns at 12 sq. metres per litre
Usual no. of coats	3-4
Abrasion resistance	Excellent
Chemical resistance	Very good
Heat resistance	Very good - 100°C
Solvent resistance	Excellent
Toxicity	Contains xylol and small amounts of monomeric di-isocyanate
Durability	Excellent (interior)
Thinning and clean up	Do not thin; clean up with Resene Polythane Brush Cleaner
VOC	c. 600 grams per litre (see Resene VOC Summary)

Physical properties

Performance

1. May be applied over a wide range of temperatures (10°C - 30°C).
2. Excellent intercoat adhesion provided there is no longer than 24 hours between coats.
3. Excellent curing by positive reaction with traces of atmospheric moisture.
4. Requires no thinning.
5. Extremely good slip resistance.

Limitations

1. Due to its unique mode of curing, pot life is very susceptible to atmospheric moisture. Pot life may be prolonged by:
 - a) Keeping lids on the tins.
 - b) Discarding unused residue from the roller trays.
 - c) Decanting remains of Resene Polythane into smaller tins to reduce ullage.

Pot life varies according to humidity at the time of use and cannot be accurately predicted. Viscosity is the most sensitive indicator and as soon as Resene Polythane becomes too thick to be applied it must be discarded.
2. Must not be sprayed.

Polythane clear polyurethane

Surface preparation

New cork, fibre and particle board, parquet, wood flooring

Thoroughly sand and vacuum. Ensure surface is dry and free of dust, oil, grease and foreign matter. Seal fibre and particle board with one full coat of Resene Particle Board Sealer (see [Data Sheet D43](#)) taking care not to overspread.

Previously varnished

Thoroughly sand and vacuum to remove all gloss, dust and grease. Ensure all old floor polishes are removed, paying particular attention to the gaps in tongue and groove flooring.

Caution

Sanding dusts from some hardwoods are considered carcinogenic, and all old timber sanding dusts should be considered potentially harmful. Always wear an efficient dust mask.

Sanding dust from old lead or chromate based paints or old building materials containing asbestos may be injurious to the health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.

Application

Apply by brush or short pile roller. Do not spray. DO NOT THIN.

1. Apply one generous coat of Resene Polythane. Allow to dry for three hours or until touch dry.
2. Apply one coat of Resene Polythane and leave overnight. Lightly sand and vacuum clean.
3. Apply one to two coats of Resene Polythane. A total of four coats will give a finer finish than three coats.
4. Allow 48 hours before allowing traffic on the finished floor.

Precautions

1. FLAMMABLE - Keep away from heat and open flame. Keep closed when not in use.
2. Avoid breathing vapour - use with adequate ventilation.
3. Wear protective clothes. Avoid skin contact. If any skin contact occurs, wash skin thoroughly with soap and water immediately. Do not scrub the skin.
4. Avoid direct draught on finish coats during drying.
5. Do not use Resene Polythane Brush Cleaner as a thinner.
6. Must not be sprayed.
7. Contains isocyanate. When sprayed this product may be harmful by inhalation. Wear suitable clothing, gloves and eye/face protection, including suitable breathing protection such as air-supplied respirator or hood. Do not breathe vapour or spray mist. Refer Resene Putting your safety first brochure.
8. If eyes become contaminated, flood with running water for at least 15 minutes. SEEK MEDICAL AID.
9. Ensure brushes/rollers are thoroughly dry or well rinsed out in Resene Thinner No.6 before use.

Please ensure the current Data Sheet is consulted prior to specification or application of Resene products. If the surface you propose to coat is not referred to by this Data Sheet, please contact Resene for clarification.

In Australia
PO Box 785, Ashmore City, Queensland 4214
Call 1800 738 383, visit www.resene.com.au
or email advice@resene.com.au

Resene
the paint the professionals use

In New Zealand
PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Call 0800 RESENE (737 363), visit www.resene.co.nz
or email advice@resene.co.nz