

Resene Paint Systems - Fire Ratings



The listed Resene paint systems over the listed substrate have been fire tested using a cone calorimeter in accordance with ISO 5660 to determine Group Classification in accordance with New Zealand Building Code (NZBC) Verification Method C/MM2 Appendix A; National Construction Code (NCC) Volume One Specification C1.10 and A2.4 of the Building Code of Australia

Substrate	Undercoat (1 coat unless otherwise stated)	Topcoat (2 coats unless otherwise stated)	Indicated Group No.	Test Report
10mm Paperfaced Plasterboard	Resene Broadwall Waterborne Wallboard Sealer (SR 10 sqm/L)	Resene SpaceCote Low Sheen (SR 15 sqm/L)	1-S (NZBC) 1 (NCC)	FH4967
10mm Paperfaced Plasterboard	Resene Broadwall Waterborne Wallboard Sealer (SR 10 sqm/L)	Resene SpaceCote Flat (SR 15 sqm/L)	1-S (NZBC) 1 (NCC)	FH4967
10mm Paperfaced Plasterboard	Resene Broadwall Waterborne Wallboard Sealer (SR 10 sqm/L)	Resene Zylone Sheen (SR 15 sqm/L)	1-S (NZBC) 1 (NCC)	FH4967
10mm Paperfaced Plasterboard	Resene Broadwall Waterborne Wallboard Sealer (SR 10 sqm/L)	Resene Ceiling Paint (SR 12 sqm/L)	1-S (NZBC) 1 (NCC)	FH4967
10mm Paperfaced Plasterboard	Resene Sureseal (SR 15 sqm/L)	Resene SpaceCote Flat (SR 14 sqm/L)	1-S (NZBC) 1 (NCC)	7-593235-CO
10mm Paperfaced Plasterboard	Resene Sureseal (SR 15 sqm/L)	Resene Lustacryl (SR 14 sqm/L)	1-S (NZBC) 1 (NCC)	7-593262-CO
13mm Paperfaced Plasterboard	Resene Broadwall Waterborne Wallboard Sealer (SR 11 sqm/L)	Resene ClinicalCote Satin (SR 14 sqm/L)	1-S (NZBC) 1 (NCC)	FH4925
13mm Paperfaced Plasterboard	Resene Broadwall Waterborne Wallboard Sealer (SR 11 sqm/L)	Resene ClinicalCote Low Sheen (SR 15 sqm/L)	1-S (NZBC) 1 (NCC)	FH4925
13mm Paperfaced Plasterboard	Resene Broadwall 3 in 1 (SR 2.5 sqm/L)	Resene ClinicalCote Satin (SR 14 sqm/L)	1-S (NZBC) 1 (NCC)	FH4925
13mm Paperfaced Plasterboard	Resene Broadwall 3 in 1 (SR 2.5 sqm/L)	Resene ClinicalCote Low Sheen (SR 15 sqm/L)	1-S (NZBC) 1 (NCC)	FH4925
13mm Paperfaced Plasterboard	Resene Broadwall Surface Prep & Seal (SR 6 sqm/L)	Resene ClinicalCote Satin (SR 14 sqm/L)	1-S (NZBC) 1 (NCC)	FH4925
13mm Paperfaced Plasterboard	Resene Broadwall Surface Prep & Seal (SR 6 sqm/L)	Resene ClinicalCote Low Sheen (SR 15 sqm/L)	1-S (NZBC) 1 (NCC)	FH4925
13mm Paperfaced Plasterboard	Resene Broadwall 3 in 1 (2 coats) (SR 7 sqm/L)	-	1-S (NZBC) 1 (NZBC)	FAR3981
13mm Paperfaced Plasterboard	Resene Broadwall 3 in 1 (SR 7 sqm/L)	Resene Zylone Sheen VOC Free (SR 16 sqm/L)	1-S (NZBC) 1 (NZBC)	FAR3981
13mm Paperfaced Plasterboard	Resene Broadwall 3 in 1 (SR 7 sqm/L)	Resene SpaceCote Low Sheen (SR 16 sqm/L)	1-S (NZBC) 1 (NZBC)	FAR3981
13mm Paperfaced Plasterboard	Resene Waterborne Smooth Surface Sealer (SR 12 sqm/L)	Resene SpaceCote Low Sheen (SR 16 sqm/L)	1-S (NZBC) 1 (NZBC)	FAR3981
13mm Paperfaced Plasterboard	Resene Broadwall Waterborne Wallboard Sealer (SR 10 sqm/L)	Resene Ceiling Paint (SR 12 sqm/L)	1-S (NZBC) 1 (NZBC)	FAR3981
6mm Fibre Cement Board	Resene Quick Dry (SR 12 sqm/L)	Resene Uracryl 802 (SR 16 sqm/L)	1-S (NZBC) 1 (NCC)	FH5139*
6mm Fibre Cement Board	Resene Quick Dry (SR 12 sqm/L)	Resene Uracryl 803 (SR 16 sqm/L)	1-S (NZBC) 1 (NCC)	FH5139*
6mm Fibre Cement Board	Resene Sureseal (SR 12 sqm/L)	Resene Uracryl 802 (SR 16 sqm/L)	1-S (NZBC) 1 (NCC)	FH5139*

6mm Fibre Cement Board	Resene Sureseal (SR 12 sqm/L)	Resene Uracryl 803 (SR 16 sqm/L)	1-S (NZBC) 1 (NCC)	FH5139*
8mm MDF	Resene Quick Dry (SR 12 sqm/L)	Resene Fireguard (SR 3.5 sqm/L)	3 (NZBC) 3 (NCC)	FH5137
8mm MDF	Resene Quick Dry (SR 12 sqm/L)	Resene Fireguard (SR 3.5 sqm/L), Resene SpaceCote Low Sheen (SR 14 sqm/L)	3 (NZBC) 3 (NCC)	FH5137
18mm MDF	Resene Quick Dry (SR 12 sqm/L)	Resene Fireguard (SR 3.5 sqm/L)	3 (NZBC) 3 (NCC)	FH5137
18mm MDF	Resene Quick Dry (SR 12 sqm/L)	Resene Fireguard (SR 3.5 sqm/L), Resene SpaceCote Low Sheen (SR 14 sqm/L)	3 (NZBC) 3 (NCC)	FH5137
9mm thick 'A' grade plywood	Resene Aquaclear Semi-Gloss	Resene Aquaclear Semi-Gloss (3 coats SR 12 sqm/L)	3 (NZBC)	FAR3981
≥ 26mm Metrapanel	Pre-primed	Resene Fireguard (SR 1 sqm/L), Resene SpaceCote Low Sheen (SR 16 sqm/L)	1-S (NZBC) 1 (NCC)	FH5334

Notes:

Test reports give the Group rating determined by application of a paint system to a given substrate thickness. The same Group rating applies to the paint system applied to greater thicknesses of the substrate given in the test report.

The Group rating of a given substrate coated with a standard 3 coat acrylic paint system will be the same as the uncoated substrate.

FH5139*

It is considered that the resulting Group Classifications achieved by paint systems on fibre cement substrates would not be adversely affected if applied to a concrete substrate. Paint system applied at coverage rates not less than the minimum specified for the fibre cement substrate.

31 Jan 2014