

net contents 1 litre (Includes tinters in base)

Must be mixed with ArmourCat Hardener in the correct volume ratio.

LLAC80501 7/08

WARNING

Read label before use. Keep out of reach of children. This material may be harmful if swallowed, inhaled or absorbed through the skin and may cause skin or eye irritation.

PRECAUTIONS

AVOID BREATHING VAPOUR - ESPECIALLY DURING EARLY STAGES OF PREGNANCY. USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C–20°C or at a cool, constant temperature. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods for cleaning equipment and disposing of unwanted paint. Do not contaminate any water supply.

FIRST AID

SWALLOWED: If ingested give water to dilute. Do not cause vomiting. Get medical attention without delay.

SKIN: If significant skin contact occurs wash skin thoroughly with soap and water. Do not scrub skin.

EYES: Hold open and flood with water for at least 15 minutes. Get medical attention without delay.

INHALATION: Remove to fresh air. IF BREATHING DIFFICULT GET MEDICAL ATTENTION IMMEDIATELY.

When seeking medical advice take this container with you.

Further information can be obtained from

AUST: NATIONAL POISONS CENTRE 1800 131 126

or from the Resene Help Line 1800 738 383.

NZ: NATIONAL POISONS CENTRE (03) 474 7000

or from the Resene Help Line (0800) 737 363.

CONTAINS: Xylene 38 gms/L.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet RA84.

SPILLS: Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible on to newspaper before washing out brushes/rollers with the recommended thinner. Do not allow thinner to enter any drains. Refer to your local Council for disposal of dirty thinner.

FIRE: Use foam, carbon dioxide or dry chemical powder.

POISON

KEEP OUT OF REACH OF CHILDREN

Resene

ArmourCat 805

pigmented sealer/undercoat base

Engineered Coating Systems



9 418022 027478

**PALE
GREY**

Resene ArmourCat 805 is a two pack, tintable acid-catalysed sealer/undercoat for priming composite boards and timbers prior to application of Resene ArmourCat metallic and solid colours. Exhibits quick drying; excellent filling and sanding characteristics.

General

• Safety Data Sheet (SDS) is available and must be consulted before use.

• In every case it is recommended that the current Resene Data Sheet is consulted for product data and surface preparation information.

• This product comprises a Base and Hardener, which must be mixed in the required ratio using an air or explosion-proof power mixer before application. Mix each component separately before blending them together. Add the total contents of the Hardener container to the total contents of the Base container. Once uniformly mixed, allow to stand for the recommended induction time prior to re-mixing and use.

• Thinning requirements may vary according to application method, equipment and environmental conditions.

• If thinning is required add recommended thinner after components have been blended and thoroughly re-mix using the power mixer.

• Ensure correct wet film thickness is applied to achieve desired dry film thickness. Allowance must be made for any thinner added.

• Use of incorrect thinner may have an adverse effect on application and performance.

• Drying is affected by low temperatures and high humidity.

• Ensure that the mixed product is used within the stated pot life. The pot life of the mixed product is given for a specific temperature. Higher temperatures will reduce the pot life, conversely lower temperatures will increase it.

• The temperature of the substrate should be 3°C above the "Dew Point".

• The "Dew Point" requirement can be presumed to be satisfied if a thin clearly defined film of water applied to the cleaned surface with a damp cloth evaporates within 15 minutes.

• Following appropriate preparation, all surfaces must be dry and clean prior to painting.

• This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, contact your local Resene ColorShop or Reseller for your nearest Technical Representative.

Be PaintWise

For tips on minimising the impact of your decorating on the environment see the Resene website.

**FLAMMABLE LIQUID
AND VAPOUR**

Keep away from heat and open flame.
Keep closed when not in use.



UN No. 1263 - Paint

Resene

the paint the professionals use

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 785, Ashmore City, Queensland, 4214
Phone 1800 738 383 Fax 1800 064 960
Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Phone (04) 577 0500 Fax (04) 577 0600
Email advice@resene.co.nz or visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

Quick check

Name: Resene ArmourCat 805.

Generic type: Acid catalysed alkyd urea resin system.

Colours: Pale Grey.

Finish: Matt.

Sealer/undercoat required: New MDF/Wood – No.

Application method: Spray application only – refer Resene Automotive before commencing work.

Mixing ratio: 5 parts Base: 1 part Hardener (by volume).

Induction time: 5-15 minutes.

Pot life: 8 hours @ 18°C. Increased temperatures will shorten pot life.

Volume solids: (Mixed, unthinned): 47%.

Theoretical coverage: 10 square metres per litre per coat. Coverage rates will vary according to substrate porosity.

Dry time (minimum): Tack free: 10-15 mins @ 18°C.
To sand: 2 hours @ 18°C.

Recoat: Minimum: 2 hours @ 18°C.
Maximum: 7 days @ 18°C.

Drying is affected by low temperatures and high humidity

Thinning and clean up: Resene Thinner No.15.

Resene Data Sheet: RA84.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy. In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that the colour in this container is the same as selected. Resene accepts no responsibility for the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 RESENE (NZ) or visit the Resene website.