

# Armourchlor AM-ZP primer finish coat

interior chlorinated rubber  
**Engineered Coating Systems**



**WARNING**  
KEEP OUT OF REACH OF CHILDREN



WHITE

LL49620F 3/10

**WARNING**

Read label before use. Keep out of reach of children. This material may be harmful if swallowed, inhaled or absorbed through the skin. Causes skin and eye irritation. May cause an allergic skin reaction. May damage fertility or the unborn child. May damage organs through prolonged or repeated exposure. Toxic to the aquatic environment with long lasting effects.

**PRECAUTIONS**

**AVOID BREATHING VAPOUR – ESPECIALLY DURING EARLY STAGES OF PREGNANCY. USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.**

Do not handle until all safety precautions have been read and understood. Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Do not contaminate any water supply. Ground/bond container and receiving equipment, as product is volatile and may generate a hazardous atmosphere. Take precautionary measures against static discharge. Use explosion-proof electrical/ventilating/lighting and other equipment. Use only non-sparking tools. Store locked up. Wear protective gloves and eye/face protection and any other personal protective equipment as required. Do not allow contaminated clothing from the workplace. Wash thoroughly after handling. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods for cleaning equipment and disposing of unwanted paint. Avoid release to environment.

**FIRST AID**

**SWALLOWED:** If ingested give water to dilute. Do not cause vomiting. Get medical attention without delay.

**IF ON SKIN (or hair):** Remove/take off all contaminated clothing and wash before re-use. Wash skin with plenty of soap and water/shower. If skin irritation or rash occurs get medical advice/attention.

**IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do so. Continue rinsing. If eye irritation persists, get medical advice/attention.

**INHALATION:** Remove to fresh air. IF BREATHING DIFFICULT GET MEDICAL ATTENTION IMMEDIATELY. Call a POISON CENTRE if you feel unwell.

When seeking medical advice take this container with you.

Further information can be obtained from  
AUST: NATIONAL POISONS CENTRE 131 126

or from the Resene Help Line 1800 738 383.  
NZ: NATIONAL POISONS CENTRE (03) 474 7000

or from the Resene Help Line (0800) 737 363.  
CONTAINS: Benzene dimethyl 200-300 gms/L.

Epoxy resin <50 gms/L.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet RA62.

**SPILLS:** Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

**CLEANING PAINT EQUIPMENT:** Brush/roll out as much paint as possible on to newspaper before washing out brushes/rollers with the recommended thinner. Do not allow thinner to enter any drains. Refer to your local Council for disposal of dirty thinner.

**FIRE:** Use foam, carbon dioxide or dry chemical powder.

Resene Armourchlor AM-ZP is a tough, self-priming corrosion inhibiting finish coat based on zinc phosphates and chlorinated rubber for use on suitably prepared interior metal surfaces.

**General**

- Safety Data Sheet (SDS) is available and must be consulted before use.
- In every case it is recommended that the current Resene Data Sheet is consulted for product data and surface preparation information.
- This product must be thoroughly mixed before use. Efficient mixing at all stages requires power mixing with an air or explosion proof mixer until uniformly blended.
- Thinning requirements may vary according to application method, equipment and environmental conditions.
- If thinning is required thoroughly re-mix using the power mixer.
- Ensure correct wet film thickness is applied to achieve desired dry film thickness. Allowance must be made for any thinner added.
- Use of incorrect thinner may have an adverse effect on application and performance.
- Drying is affected by low temperatures and high humidity.
- The temperature of the substrate should be 3°C above the "Dew Point".
- The "Dew Point" requirement can be presumed to be satisfied if a thin clearly defined film of water applied to the cleaned surface with a damp cloth evaporates within 15 minutes.
- Following appropriate preparation, all surfaces must be dry and clean prior to painting.
- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, contact your local Resene ColorShop or Reseller for your nearest Technical Representative.

**Be PaintWise**

For tips on minimising the impact of your decorating on the environment see the Resene website.

**FLAMMABLE LIQUID AND VAPOUR**

Keep away from ignition sources such as heat/sparks/open flame/hot surfaces.  
No smoking.

UN No. 1263 – Paint related material

**Resene**

the paint the professionals use

**In Australia:** Resene Paints (Aust) Limited  
7 Production Ave, PO Box 785, Ashmore City, Queensland, 4214  
Phone 1800 738 383 Fax 1800 064 960  
Email advice@resene.com.au or visit [www.resene.com.au](http://www.resene.com.au)

**In New Zealand:** Resene Paints Limited  
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045  
Phone (04) 577 0500 Fax (04) 577 0600  
Email advice@resene.co.nz or visit [www.resene.co.nz](http://www.resene.co.nz)

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAJ, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

**Quick check**

**Name:** Resene Armourchlor AM-ZP.

**Generic type:** Self-priming chlorinated rubber finish coat.

**Colours:** White, selected BSS 381C, 2660, 5252, Resene Total Colour System and White Colours.

**Finish:** Low sheen.

**Application method:** Airless or conventional spray.

**Recommended dry film thickness (D.F.T.):** 75 microns per coat.

**Theoretical coverage:** 6.3 square metres per litre @ 75 microns D.F.T.

**Dry time (minimum):** Touch: 2 hours @ 18°C. Drying is affected by low temperatures and high humidity. Do not apply under damp conditions.

**Recoat time:** Minimum: 12 hours @ 18°C.

**Thinning and clean up:** Resene Thinner No.6.

**Resene Data Sheet:** RA62.

**Limitations:** Interior use only. Poor resistance to aromatic solvents. Not resistant to vegetable oils or animal fats. Will soften at temperatures over 50°C.

**Overcoating:** Not normally required, however gloss level can be increased by application of gloss alkyd topcoat.

**Enjoy the Resene Promise of quality** on premium paints. See your Resene ColorShop or the Resene website for a copy.

**In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.**

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 RESENE (NZ) or visit the Resene website.