

DANGER

KEEP OUT OF REACH OF CHILDREN

Resene

Armourcote 210 hi-build primer

A-LL428304G 4/15

WARNING

Read label before use. Keep out of reach of children. Harmful if swallowed. Harmful if inhaled. Causes skin irritation. Causes serious eye irritation. Suspected of causing cancer. May damage fertility or the unborn child. May cause respiratory irritation. Harmful to aquatic life with long lasting effects.

PRECAUTIONS

AVOID BREATHING DUST, FUMES, GAS, MISTS, VAPOURS, SPRAYS. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well-ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Store locked up. Use only outdoors or in a well-ventilated area. Wear protective gloves and clothing, eye and face protection. Avoid release to the environment. Ground or bond container and receiving equipment. Use explosion-proof electrical, ventilating, lighting and intrinsically safe equipment. Use only non-sparking tools. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods for cleaning equipment and disposing of unwanted paint.

FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE, doctor, physician or first aider if you feel unwell.

IF ON SKIN (or hair): Wash with plenty of soap and water. Take off immediately all contaminated clothing.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue rinsing. If eye irritation persists: Get medical attention/advice.

IF INHALED: Remove to fresh air and keep at rest in a position comfortable for breathing.

If exposed or concerned: Get medical advice/attention.

If medical attention is required: have product container or label at hand.

Further information can be obtained from

AUST: POISONS INFORMATION CENTRE 131 126

or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)

or call Resene 0800 737 363.

CONTAINS: Xylene 15-150 gms/L, N-Butyl Acetate 15-150 gms/L, Barium Metaborate 15-150 gms/L, Zinc Oxide 15-150 gms/L, Methyl Ketoxime <5 gms/L.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet RA35.

SPILLS: Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible on to newspaper before washing out brushes/rollers with the recommended thinner. Do not allow thinner to enter any drains. Refer to your local Council for disposal of dirty thinner.

IN CASE OF FIRE: Use foam, carbon dioxide or dry chemical powder.

Engineered Coating Systems



GREY

Resene Armourcote 210 is a single-pack, high-build inhibitive primer for general industrial and non-immersion marine use. Suitable for overcoating with a wide range of protective and decorative topcoat systems.

General

• Safety Data Sheet (SDS) is available and must be consulted before use.

• In every case it is recommended that the current Resene Data Sheet is consulted for product data and surface preparation information.

• This product must be thoroughly mixed before use. Efficient mixing at all stages requires power mixing with an air or explosion proof mixer until uniformly blended.

• Thinning requirements may vary according to application method, equipment and environmental conditions.

• If thinning is required thoroughly re-mix using the power mixer.

• Ensure correct wet film thickness is applied to achieve desired dry film thickness. Allowance must be made for any thinner added.

• Use of incorrect thinner may have an adverse effect on application and performance.

• Drying is affected by low temperatures and high humidity.

• The temperature of the substrate should be 3°C above the "Dew Point".

• The "Dew Point" requirement can be presumed to be satisfied if a thin clearly defined film of water applied to the cleaned surface with a damp cloth evaporates within 15 minutes.

• Following appropriate preparation, all surfaces must be dry and clean prior to painting.

• This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, contact your local Resene ColorShop or Reseller for your nearest Technical Representative.

Be PaintWise

For tips on minimising the impact of your decorating on the environment see the Resene website.



UN NO. 1263 - PAINT RELATED MATERIAL

FLAMMABLE LIQUID AND VAPOUR

Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.



Resene

the paint the professionals use



In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 924, Beenleigh, Qld 4207
Phone 1800 738 383 Fax 1800 064 960
Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Phone (04) 577 0500 Fax (04) 577 0600
Email advice@resene.co.nz or visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. This product complies with all the requirements of an APAS Paint Specification. Refer to the APAS Specification list on the Resene website for full details. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

net contents 4 litres

Quick check

Name: Resene Armourcote 210.

Generic type: Modified alkyd.

Colour: Grey, Red Oxide.

Finish: Low sheen.

Application method: Airless or conventional spray.

Recommended dry film thickness (D.F.T.): 50-75 microns per coat.

Theoretical coverage: 12 square metres per litre per coat at 50 microns D.F.T. 8 square metres per litre per coat at 75 microns D.F.T.

Dry time (minimum): Touch dry: 20 minutes at 21°C. Hard dry: 6 hours at 21°C. Drying is affected by low temperatures and high humidity.

Recoat time: Minimum: 24 hours. Maximum: 1 month (epoxies, alkyds, vinyls and acrylics); 1 week (two pack polyurethanes). Recoat times are for recoating at 21°C. Recoat times will be shorter at higher temperatures.

Thinning and clean up: Resene Thinner No.6.

Resene Data Sheet: RA35.

Limitations: Not designed for long term exterior exposure without topcoating. Adhesion of alkyd finishes may vary according to topcoat formulation. Establish adhesion properties of the system by application of a test area.

Overcoating: Epoxies, polyurethanes, vinyls, alkyds and acrylics. To avoid adhesion issues early topcoating is recommended.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.