

WARNING

Read label before use. Keep out of reach of children. Causes skin irritation. Causes eye irritation. May damage fertility or the unborn child. May cause respiratory irritation. Toxic to the aquatic environment with long-lasting effects.

PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Do not handle until all safety precautions have been read and understood. Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Store locked up. Ground/bond container and receiving equipment. Take precautionary measures against static discharge. Use explosion-proof electrical/ventilating/lighting equipment. Use only non-sparking tools. Wear protective gloves and eye/face and respiratory protection. Avoid release to the environment. Dispose of empty container safely. Clean up spillage. Consult Resene checklist on environmentally acceptable methods for cleaning equipment and disposing of unwanted paint.

FIRST AID

IF SWALLOWED: Rinse mouth.

IF ON SKIN (or hair): Remove/take off all contaminated clothing and wash before re-use. Wash skin with plenty of soap and water/shower. If skin irritation or rash occurs get medical advice/attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do so. Continue rinsing. If eye irritation persists: Get medical attention/advice.

IF INHALED: Remove to fresh air and keep at rest in a position comfortable for breathing.

If exposed or concerned, seek medical advice.

When seeking medical advice take this container with you.

Further information can be obtained from

AUST: POISONS INFORMATION CENTRE 131 126

or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)

or call Resene 0800 737 363.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet RA30A.

SPILLS: Use appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible on to newspaper before washing out brushes/rollers with the recommended thinner. Do not allow thinner to enter any drains. Refer to your local Council for disposal of dirty thinner.

IN CASE OF FIRE: Use foam, CO₂, dry chemical for extinction.

DANGER

KEEP OUT OF REACH OF CHILDREN

Resene**Rust-Arrest
anti-corrosive primer****Engineered Coating Systems**

Resene Rust-Arrest is a lead and chromate free primer developed for use on steel where optimum surface preparation is not practical. Resene Rust-Arrest has good surface wetting properties and protects via passivating pigments.

General

- Safety Data Sheet (SDS) is available and must be consulted before use.
- In every case it is recommended that the current Resene Data Sheet is consulted for product data and surface preparation information.
- The paint must be thoroughly mixed before use. Efficient mixing at all stages requires power mixing with an air or explosion proof mixer until uniformly blended.
- Thinning requirements may vary according to application method, equipment and environmental conditions. Excessive thinning will reduce the dry film build and may result in the appearance of runs or sags in the coating.
- After thinning thoroughly re-mix using the power mixer.
- Ensure correct wet film thickness is applied to achieve required dry film thickness. Allowance must be made for any thinner added.
- Use of incorrect thinner may have adverse effect on application and performance.
- Drying is affected by low temperatures and high humidity.
- The temperature of the substrate should be 3°C above the "Dew Point".
- The "Dew Point" requirement can be presumed to be satisfied if a thin clearly defined film of water applied to the cleaned surface with a damp cloth evaporates within 15 minutes.
- Following appropriate preparation, all surfaces must be dry and clean prior to painting.
- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, contact your local Resene ColorShop or Reseller for your nearest Technical Representative.

Be PaintWise

For tips on minimising the impact of your decorating on the environment see the Resene website.

**FLAMMABLE LIQUID**

3

UN No. 1263

– PAINT RELATED MATERIAL

FLAMMABLE LIQUID AND VAPOURKeep away from heat/sparks/open flames/
hot surfaces. No smoking**Resene**
the paint the professionals use

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 924, Beenleigh, Qld 4207
Phone 1800 738 383 Fax 1800 064 960
Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Phone (04) 577 0500 Fax (04) 577 0600
Email advice@resene.com.nz or visit www.resene.com.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

Quick check

Name: Resene Rust-Arrest.

Generic type: Alkyd anti-corrosive primer (inhibitive).

Colour: Red oxide.

Finish: Low sheen.

Application method: Brush, roller or conventional spray.

Recommended dry film thickness (D.F.T.): 40–50 microns per coat.

Theoretical coverage: 13.75 square metres per litre per coat at 40 microns D.F.T. 11 square metres per litre per coat at 50 microns D.F.T.

Dry time (minimum): Surface dry: 4 hours at 18°C. Hard dry: 24 hours at 18°C. Drying is affected by low temperatures and high humidity.

Recoat time (minimum): Acrylic/alkyd: 24 hours at 18°C (minimum), one month (maximum). Sanding of Resene Rust-Arrest is required if recoating beyond maximum recoating time.

Usual number of coats: 1 (2 for severe exposure or when topcoating with an acrylic system).

Thinning and clean up: Resene Thinner No.10 (brush/roller application); Resene Thinner No.12 (spray application).

Resene Data Sheet: RA30A.

Limitations: Do not apply directly to zinc rich surfaces, such as bare galvanised steel, Zinalume, or zinc primers. Not recommended for immersion service. Not designed for exterior exposure without overcoating.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy. **In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.**

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.