

Resene Industrial SRG Grit

slip-resistant additive 2kg

Designed for giving slip resistance to high build industrial products
such as Resene Armourcote 512 and Armourcote 510.

Keep closed when not in use.

WARNING
KEEP OUT OF REACH OF CHILDREN



LL844002F 9/22

SAFETY PRECAUTIONS

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation.

PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions.

FIRST AID: IF SWALLOWED: Rinse mouth. Call a POISON CENTRE, doctor or first aider if you feel unwell.

IF ON SKIN (or hair): Rinse skin with plenty of soap and water. If skin irritation or rash occurs get medical advice or attention.

IF IN EYES: Rinse cautiously with water for several minutes. If eye irritation persists get medical advice or attention.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing. If medical advice is required have product container or label at hand.

Further information can be obtained from AUST: POISONS INFORMATION CENTRE 131 126 or call Resene 1800 738 383. NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766) or call Resene 0800 737 363. When disposing product, avoid generating airborne dust. Refer to local waste management authority.

Contains: Aluminium oxide.

General:

Prepare and prime surface to be painted according to individual product recommendations (refer to appropriate Data Sheets for technical data and specifications prior to use of the floor coating chosen).

Mixing:

Keep closed when not in use. Add 500g of Resene Industrial SRG Grit per litre of paint. The addition of higher levels of grit is not recommended due to adverse effects on product characteristics. If in doubt, trial a small patch before painting entire area. Mix thoroughly until perfectly homogeneous. The addition of Resene Industrial SRG Grit will result in an increase in total paint volume of about 20%. As a result a large container for mixing is recommended.

Application:

Mixed product is best applied by roller. Apply one coat of Resene Industrial SRG Grit modified coating followed by a second coat of unmodified product. Recoat times will be extended due to the thicker film. Use a pour and spread application technique to facilitate even distribution of the aggregate across the substrate. Ensure the Resene Industrial SRG modified coat is well mixed at all times to keep the aggregate in suspension.

Coverage:

Coverage of grit modified coating can be up to 50% less than unmodified product. Due allowance must be made for this when estimating quantities.

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 918, Ashmore City, QLD 4214
Ph 1800 738 383 Visit resene.com.au

In New Zealand: Resene Paints Limited
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045
Ph (04) 577 0500 Visit resene.co.nz



SRG Industrial
Grade SDS