

KEEP OUT OF REACH OF CHILDREN

Resene

Sandtex

mediterranean effect

exterior/interior

net
contents
4 litres
tinter included

A-LL70404 11/12

WARNING

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation.

PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods of cleaning equipment and disposing of unwanted paint. Do not contaminate any water supply. Avoid release to the environment.

FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE or doctor/physician if you feel unwell.

IF ON SKIN (or hair): Remove/take off all contaminated clothing and wash before re-use. Rinse skin with plenty of soap and water/shower. If skin irritation or rash occurs: Get medical advice/attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do so. Continue rinsing. If eye irritation persists: Get medical attention/advice.

When seeking medical advice take this container with you. Further information can be obtained from AUST: POISONS INFORMATION CENTRE 131 126 or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766) or call Resene 0800 737 363.

For use as a decorative/protective coating. For full technical instructions see Data Sheet D71.

SPILLS: Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways.

Resene Sandtex is a tough waterborne texture finish for beautifying and protecting concrete structures. A 150 micron texture with the ability to recreate the texture of natural sandstone. An excellent basecoat for Resene Paint Effects Medium as the texture adds an extra dimension to the effect. Available in Standard and Superfine variants. May be overcoated with Resene Multishield+ (see Data Sheet D54a) to give a hard finish that is self-cleansing and virtually indestructible.

Preparation

- Ensure surfaces to be coated are in sound condition, dry, free from dirt, dust, loose material and salt. Remove accumulated windblown salt by washing with Resene Paint Prep and Housewash (see Data Sheet D812).
- Waterblasting is the best surface preparation prior to coating of weathered cementitious surfaces, galvanised steel and Zinalume.
- If mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80).
- Efflorescence on masonry **must be treated** (see Data Sheet D83).
- Wherever oil and grease are present ensure the surface to be coated is thoroughly cleaned using Paint Prep and Housewash. Flush clean with water.
- For heavy contamination scrub down with Resene Emulsifiable Solvent Cleaner (see Data Sheet D804) then rinse clean with water.
- All loose powdery material must be removed. If waterblasting is not possible thoroughly wire brush.
- **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old asbestos containing building materials may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**
- Fill cracks larger than 1 mm in cementitious surfaces with a suitable elastomeric paintable sealant after priming with Resene Sureseal (see Data Sheet D42).
- Fill cracks and holes in interior walls before sealing.

This product may be used to coat a wide variety of surfaces. If the surface you propose to coat is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or Reseller for advice.

Priming

- All surfaces that are in poor condition or affected by efflorescence or which are friable, powdery or chalky must be primed with Resene Sureseal.
 - Sealants - special coating requirements of construction sealants and fillers should be followed.
 - Sound cementitious surfaces do not normally require a primer. Glossy surfaces may require treatment with Resene Waterborne Smooth Surface Sealer (see Data Sheet D47a).
 - Plasterboard must be prepared to an appropriate level of finish. Either Resene Broadwall Surface Prep & Seal (see Data Sheet D807), Resene Broadwall 3 in 1 (see Data Sheet D810) or Resene Sureseal followed by lining paper is recommended in critical lighting areas.
 - Hardboard must be sealed (e.g. Resene Sureseal - see Data Sheet D42) to promote flow of the topcoats. Use Resene Sureseal if the surface is water stained or if condensation is likely to form on the surface.
 - Some 'soft' plasterboard preparatory products and undercured gypsum based stoppings may not be suitable basecoats for painting under stressed conditions. Reinforcement with a saturation coat of a fully penetrating primer (such as Resene Sureseal) may be required. Use Resene Sureseal or Resene StainLock (see Data Sheet D408) if the surface is water stained or has yellowed due to prolonged exposure to sunlight.
 - Galvanised steel or Zinalume should not be allowed to weather. Apply one coat of Resene Galvo One (see Data Sheet D41) or Resene Galvo-Prime (see Data Sheet D402) as soon as possible. If the galvanised steel or Zinalume has weathered use only Resene Galvo One.
- #### Application
- Prepare and prime surface as per schedule above.
 - With all application methods, a basecoat of Resene Lumbersider

(see Data Sheet D34) or Resene X-200 (see Data Sheet D62) tinted to the same colour as the Resene Sandtex enhances the final appearance.

- Maintain good ventilation throughout the drying and post application curing period to ensure the paint is properly cured. This may require use of an extraction system when painting in marginal painting conditions. Do not use gas or diesel burners to heat coated area as these produce water that will inhibit drying and curing. Poor ventilation may affect appearance and performance.
- **Spray: Apply Resene Sandtex using air spray at approximate spreading rate of 4-6 sq.m/litre in smooth even passes.**
- **9mm pile roller: For a monolithic finish apply one or two coats at 4-6 sq.m/litre. Only one coat is required if a basecoat (tinted to the same colour as the Resene Sandtex) has been applied.**
- **Crows foot: To resemble brushed plaster, apply one coat of Resene Sandtex using a 9mm roller at 6 sq.m/litre and brush off in a random manner to achieve the desired effect.**

Be PaintWise

For tips on minimising the impact of your decorating on the environment see the Resene website.



Resene

the paint the professionals use



In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 924, Beenleigh, Qld 4207
Phone 1800 738 383 Fax 1800 064 960
Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Phone (04) 577 0500 Fax (04) 577 0600
Email advice@resene.co.nz or visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. Resene Sandtex Standard complies with all the requirements of an APAS Paint Specification. Refer to the APAS Specification list on the Resene website for full details. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

Quick check

Use on: Exterior and interior cementitious surfaces, solid plaster, GRC and suitably primed wallboards, galvanised steel and Zinalume.

Gloss level: Flat.

Coverage: 4-6 square metres per litre per coat. Application rates vary depending upon choice of texture and application method.

Dry time (minimum): 2 hours. Do not apply at temperatures below 10°C or when temperatures are liable to drop below this during the drying period. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 2 hours.

Primer required: Dependent upon surface.

Usual number of coats: One - sprayed; Two - rolled.

Application method: Spray, synthetic fibre roller or brush.

Thinning and clean up: Water.

Colour range: Selected Resene Total Colour System including BS5252, Multi-finish, Whites & Neutrals and The Range.

Before use: Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. When using multiple packs of this product on the same project please mix them together before use. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.



WHITE