

Resene product labels are updated from time to time. This label is provided as a guide for this product and may differ from the label on the container you purchase.
Please discuss your project with your local Resene ColorShop team or reseller to ensure you have the right products to give you the best quality finish for your specific project.

net contents 1 litre
tinter included

LL1150201 9-24

KEEP OUT OF REACH OF CHILDREN

SAFETY PRECAUTIONS

Read label before use. Keep out of reach of children. This material is quite bland; with vapour, occasional skin contact and even minor ingestion having negligible hazard. Repeated skin contact may, and any eye contact will, cause irritation. Harmful to aquatic life with long lasting effects.

PRECAUTIONS

USE WITH ADEQUATE VENTILATION. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well-ventilated area indoors, away from foodstuffs, at an ambient temperature and avoid freezing conditions. Avoid release to the environment.

FIRST AID

IF SWALLOWED: Rinse mouth. Call a POISON CENTRE, doctor or first aider if you feel unwell.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing.

IF ON SKIN (or hair): Rinse skin with plenty of soap and water. If skin irritation or rash occurs get medical advice or attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation occurs get medical advice or attention.

When seeking medical advice take this container with you. Further information can be obtained from

AUST: POISONS INFORMATION CENTRE 131 126
or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)
or call Resene 0800 737 363.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet D315S.

If using this product tinted to a Resene CoolColour™, see Data Sheet D315SC.

SPILLS: Wear appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible onto newspaper before washing brushes and rollers. Dispose of wash-up water onto grassy/unsealed area or into inside sink/basin, NOT into outside stormwater drain where it may harm fish in local waterways. See resene.com/cleanup for cleaning instructions.

Resene

Summit Roof waterborne satin

exterior



WHITE

Resene Summit Roof is a unique waterborne satin for ease of application and maximum life over properly prepared metal surfaces and cementitious roof surfaces. It's available in solid colours and metallic finishes to suit your project.

Preparation

- Ensure the surface is in sound condition, dry and free from dirt, dust, loose material, oil (including mineral oil based wood finishes or similar) and salt.
- Remove accumulated windblown salt by washing with Resene Paint Prep and Housewash (see Data Sheet D812).
- Water blasting is the best surface preparation prior to painting of weathered cementitious roof surfaces, galvanised steel and Zincalume.
- If mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80).
- Efflorescence on roof masonry **must be treated**.
- Wherever oil and grease are present and when painting galvanised steel or Zincalume, clean the surface thoroughly using Resene Roof and Metal Wash (see Data Sheet D88). Flush clean with water.
- Disconnect downpipes until after the first heavy shower of rain before using for collection of drinking water. Divert the run-off onto a garden or grassed area.
- **All sanding dusts can be harmful. Always wear appropriate protection. Seek expert advice if working with lead, chromate or asbestos based materials or surfaces.**
- Consult your Resene ColorShop or reseller for technical advice on painting of old cementitious roof tiles or if painting weathered galvanised steel and Zincalume or if corrosion is present.
- This product may be used to paint a wide variety of surfaces. If the surface you propose to paint is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or reseller for advice.

Priming

- Dark colours used on exterior surfaces are likely to increase heat and stress on the surface and, depending on the substrate, may reduce its lifespan and increase the level of coating maintenance required to maintain an acceptable visual appearance. Resene CoolColours can be used on appropriate projects to assist with heat reflectance.
- When a CoolColour variant of this product is being used, apply a primer coat of Resene Quick Dry white (see Data Sheet D45) or Resene Galvo-Prime (see Data Sheet D402) immediately below the Resene CoolColour topcoat for optimum performance. Refer to Resene ColorShop or reseller staff as to the most appropriate CoolColour system for your project.
- Galvanised steel or Zincalume does not need to weather prior to painting. Apply one coat of Resene Galvo One (see Data Sheet D41) or Resene Galvo-Prime as soon as possible. If the galvanised steel or Zincalume has weathered for more than 6 months use only Resene Galvo One. Apply Resene Galvo One by brush to full surface wetting of the substrate.
- Wash new unweathered coloured steel, such as COLORSTEEL® or COLORBOND®, with Resene Heavy Duty Paint Prep and Oil Remover (see Data Sheet D816), then prime with Resene Pre-Coated Steel Primer (see Data Sheet D413) before topcoating.
- Prime aluminium with Resene Galvo One or Resene Galvo-Prime.

- Apply a saturation coat of Resene Sureseal (see Data Sheet D42) on bare cementitious roof tiles before topcoating.
- When repainting spot prime all bare areas with one coat of Resene Galvo One. Apply by brush to ensure full surface wetting of the substrate.
- If due to climatic conditions foam persists after rolling, add 5% Resene Hot Weather Additive to Resene Galvo-Prime, roll on and lay off with a brush. Foam craters create weak spots in the protective system.

Application

- Apply two coats in the required colour by brush, roller or airless spray allowing dry time between coats.
- Prime the bare substrate when exposure of an unpainted roof exceeds six months or when there is white or red corrosion on the roof.
- For airless spray of the satin version (not for the MIOX or Commercial version), use a unit capable of achieving a flow rate of greater than 2 litres per minute, such as a Graco 395, using a FFLP 516 tip at 1800 psi with the addition of 2% Resene Summit Roof Spray Additive and a 60 mesh filter. When spraying roofs apply in a single direction from top to bottom or vice versa while maintaining a wet edge at all times. Stripe coating of vertical sections of trough section roofing may be required to achieve correct dry film thicknesses.
- Do not use Resene Summit Roof Spray Additive with Resene Wintergrade Additive or Resene Umbrella Additive.
- Maintain good ventilation throughout the drying and curing period to ensure the paint is properly cured. Poor ventilation may inhibit curing and performance.

Maintenance

(after a minimum of four weeks' drying)

See the Resene Caring for your paint finish brochure or the Resene website for full cleaning instructions.

Be PaintWise

For tips on responsible disposal of paint, cleaning equipment and minimising the impact of your decorating on the environment see the Resene website. Do not discharge any paint into the environment. Resene PaintWise (NZ) or paintback.com.au (Australia) accepts residual unwanted paint and packaging. Or contact your Local Authority for disposal information. Please recycle.



Summit Roof
Semi-Gloss SDS

Resene

the paint the professionals use



Summit Roof
Semi-Gloss SDS

In Australia: Resene Paints (Aust) Ltd
7 Production Ave, PO Box 918, Ashmore City, QLD 4214
Ph 1800 738 383 Visit resene.com.au

In New Zealand: Resene Paints Ltd
Vogel St, PO Box 38242, Wgtn Mail Centre, Lower Hutt 5045
Ph (04) 577 0500 Visit resene.co.nz

Quick check

Use on: Properly prepared metal surfaces and cementitious roof surfaces.

Gloss level: Satin.

Typical coverage: 12-14 square metres per litre per coat. The spreading rate recommended for this product will achieve hiding in two coats for most colours. Coverage may vary depending on substrate, colour, application technique and weather/temperature conditions. See the Resene website for more information.

Dry time (minimum): 45 minutes at 20°C. Do not apply at temperatures below 8°C or when temperatures are liable to drop below this during the drying period. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 2 hours at 20°C.

Primer required: Yes.

Usual number of coats: Two (brush/roller). One (airless spray, wet on wet). Bright colours may require an additional coat.

Application method: Brush, roller (Resene No.1 roller sleeve on flat surfaces or a Roof Master roller sleeve on corrugated galvanising or Zincalume) or airless spray (using a unit capable of achieving a flow rate of greater than 2 litres per minute, such as a Graco 395, using a FFLP 516 tip at 1800 psi with the addition of 2% Resene Summit Roof Spray Additive and a 60 mesh filter). Spraying metallic colours will require a professional applicator using a LTX 517 tip and 30 mesh filter.

Thinning: In hot conditions thin with up to 5% Resene Hot Weather Additive to slow drying. Spraying - add up to 2% Resene Summit Roof Spray Additive when applying over an existing dark roof colour or when the surface is too hot to touch.

Clean up: Water.

Colour range: Selected Resene Total Colour System colours. Also available as Resene Summit Roof CoolColour to help reflect heat from exterior surfaces.

Application of a Resene CoolColour will reflect more heat than the same colour made using non-cool pigmentation and reduce heat related stress on the substrate; it will not make the painted surface cool to touch. Check with Resene staff whether a Resene CoolColour is right for your project.

Before use: Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

Read the appropriate Product Data Sheet and Safety Data Sheet before use.

Please ensure that use of this product is compatible with the substrate and surface preparation method and that the colour in this container is the same as selected. When using multiple packs of this product on the same project please mix them together before use. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. Resene products are designed to be used as a system for optimal results. Substitution may cause substandard results or system failure. For further painting advice and information, call 1800 738 383 (AUST), 0800 737 363 (NZ) or visit the Resene website.