

SAFETY PRECAUTIONS

Read label before use. Keep out of reach of children. May be harmful if swallowed. Causes mild skin irritation. Causes serious eye irritation. Harmful to aquatic life with long lasting effects.

PRECAUTIONS

AVOID BREATHING DUST, FUMES, GAS, MISTS, VAPOURS, SPRAYS. DO NOT EAT, DRINK OR SMOKE WHILE USING.

Store in original or correctly labelled container, tightly closed, in a well ventilated area indoors, away from foodstuffs, either between 15°C-20°C or at a cool, constant temperature. Wear protective gloves and clothing, eye and face protection. Ground or bond container and receiving equipment. Use explosion-proof electrical, ventilating, lighting and intrinsically safe equipment. Use only non-sparking tools. Take precautionary measures against static discharge. Avoid release to the environment. Dispose of empty container safely. Consult Resene checklist on environmentally acceptable methods for cleaning equipment and disposing of unwanted paint.

FIRST AID

IF SWALLOWED: Do NOT induce vomiting. Rinse mouth. Call a POISON CENTRE or doctor if you feel unwell.

IF ON SKIN (or hair): Remove immediately any contaminated clothing. Rinse skin with water. If skin irritation occurs, get medical advice or attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do so. Continue rinsing. If eye irritation persists: Get medical advice or attention.

IF INHALED: If breathing is difficult, remove to fresh air and keep at rest in a position comfortable for breathing.

Call a POISON CENTRE, or doctor if you feel unwell.

When seeking medical advice take this container with you. If exposed or concerned: Call a POISON CENTRE.

Further information can be obtained from

AUST: POISONS INFORMATION CENTRE 131 126 or call Resene 1800 738 383.

NZ: NATIONAL POISONS CENTRE 0800 POISON (764 766)

or call Resene 0800 737 363.

CONTAINS: Ethylene Glycol Monobutyl Ether 90-180 gms/L, Propylene Glycol Monomethyl Ether – mixtures of isomers 270-550 gms/L, Naphtha Petroleum, light aromatic solvent 90-230 gms/L.

For use as a decorative/protective coating.

For full technical instructions see Data Sheet D512.

SPILLS: Use appropriate protective clothing. Absorb with sand or earth. Collect and seal in properly labelled drums. Do not allow to enter drains or to run off into waterways. Refer to local waste management authority.

CLEANING PAINT EQUIPMENT: Brush/roll out as much paint as possible on to newspaper before washing out brushes/rollers with Resene Brush Cleaner. Do not allow Resene Brush Cleaner to enter any drains. Refer to your local Council for disposal of dirty Resene Brush Cleaner.

FIRE: Use foam, carbon dioxide or dry chemical powder.

WARNING

KEEP OUT OF REACH OF CHILDREN

Resene

Walk-on Concrete Clear Wet Look

exterior protection for concrete and pavers
solventborne



CLEAR
GLOSS

Resene Walk-on Concrete Clear Wet Look is a solventborne gloss clear designed to achieve a wet look on substrates subject to pedestrian and light vehicular traffic. It penetrates into the concrete to highlight the colour patina of concrete.

Preparation

• Ensure substrates to be coated are in sound condition, dry, free from dirt, dust, loose material, oil (including mineral oil based wood finishes or similar) and salt. Remove accumulated windblown salt by washing with Resene Paint Prep and Housewash (see Data Sheet D812). If moss or mould is present, treat with Resene Moss & Mould Killer (see Data Sheet D80).
• New concrete must be allowed to cure for a minimum of 28 days before coating. Efflorescence on concrete must be treated, if the cause of efflorescence cannot be identified and corrected DO NOT apply Resene Walk-on Concrete Clear Wet Look.

• Concrete should be diamond ground or acid etched (see Data Sheet D83) prior to clear coating. Acid etching can only be used in the absence of a curing membrane. Splash water onto the surface, if the concrete does not immediately absorb the water and darken then grinding is the only surface preparation option.

• Waterblasting is the best surface preparation prior to coating of weathered cementitious surfaces.

• If oil and grease are present ensure the surface is thoroughly cleaned using Resene Heavy Duty Paint Prep and Oil Remover (see Data Sheet D816).

• **All sanding dusts may be harmful and appropriate protection must be worn. In particular dusts from old lead or chromate based paints or old building materials containing asbestos may be injurious to health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.**

• This product may be used on a wide variety of surfaces. If the surface you propose to clear coat is unsound or not referred to, try a small test area first or contact your local Resene ColorShop or Reseller for advice.

• Protect skin at all times with approved safety equipment.

Application

• Do not shake contents, rather stir well with a wide flat stirrer.

• Do not apply to a damp substrate.

• Apply one to two coats of Resene Walk-on Concrete Clear Wet Look allowing at least four hours between coats.

• Minimise overlap during brush or roller application to avoid lapmarks.

• Allow at least 24 hours after second coat before putting the area into full use.

• Take care to avoid excess film build up on top of the surface being coated to ensure best durability and resistance to mechanical damage. Trafficable areas coated with this unmodified product will not comply with the Building Act Clause D1.3.3d. SURFACES COATED WITH RESENE WALK-ON CONCRETE CLEAR WET LOOK MAY BE SLIPPERY WHEN WET.

Maintenance

(after a minimum of four weeks' drying)

• If cleaning is required, use Resene Paint Prep and Housewash correctly diluted with water and a soft broom to clean down the surface.

• Apply Resene Deep Clean (see Data Sheet D815) at the start of spring and autumn for control of algal growth.

Be PaintWise

For tips on minimising the impact of your decorating on the environment see the Resene website.



UN NO. 1263 – PAINT RELATED
MATERIAL

FLAMMABLE LIQUID AND VAPOUR

Keep away from heat, sparks, open flames
and hot surfaces. No smoking.



Walk-on
Concrete Clear
Wet Look SDS

Resene

the paint the professionals use



Walk-on
Concrete Clear
Wet Look TDS

In Australia: Resene Paints (Aust) Limited
7 Production Ave, PO Box 924, Beenleigh, Qld 4207
Phone 1800 738 383 Fax 1800 064 960
Email advice@resene.com.au or visit www.resene.com.au

In New Zealand: Resene Paints Limited
Vogel Street, PO Box 38242, Wellington Mail Centre, Lower Hutt 5045
Phone (04) 577 0500 Fax (04) 577 0600
Email advice@resene.co.nz or visit www.resene.co.nz

Manufactured under a quality system certified as complying with ISO9001 by Telarc SAI, an accredited certification body. Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001, using vegetable-based inks.

Quick check

Use on: Concrete, unglazed tiles, brick, cobblestones, driveways, paths, steps, patios, swimming pool surrounds and light industrial floors.

Gloss level: Gloss (wet look).

Coverage: Dependent upon surface porosity and profile. Typical coverage for concrete is 4.5-5.5 square metres per litre.

Dry time (minimum): 2 hours. Drying is slowed by low temperatures and high humidity. Do not apply under damp conditions.

Recoat time (minimum): 4 hours.

Primer required: No.

Usual number of coats: 1-2 (depends on substrate porosity).

Application method: Brush, short nap synthetic fibre roller or spray.

Thinning: Do not thin.

Clean up: Resene Brush Cleaner.

Colour range: Clear.

Before use: Silicone treatments may affect adhesion and penetration. A test patch is recommended. Stir well with a wide flat stirrer.

Enjoy the Resene Promise of quality on premium paints. See your Resene ColorShop or the Resene website for a copy.

In every case it is recommended that the appropriate Data Sheet and Safety Data Sheet are consulted prior to application.

Please ensure that use of this product is compatible with the substrate and surface preparation method. Resene does not accept any responsibility for the application of incorrect product to substrate or the application of incorrect colours. For further painting advice and information, call 1800 738 383 (AUST), 0800 0800 737 363 (NZ) or visit the Resene website.